

Nishant Kumar^{*1}, Ikhwan Syafiq Mohd Noor², Muhd Zu Azhan Yahya³, Satya Prakash¹

¹Department of Civil Engineering, Sharda University, Greater Noida, India;

²Physics Division, Centre of Foundation Studies for Agricultural Sciences, Universiti Putra Malaysia, UPM Serdang, Selangor Darul Ehsan, Malaysia;

³Faculty of Defence Science and Technology, Universiti Pertahanan Nasional Malaysia (UPNM), Kuala Lumpur, Malaysia.

Review Paper

ISSN 0351-9465, E-ISSN 2466-2585

<https://doi.org/10.62638/ZasMat1092>



Zastita Materijala X (X)
(2024)

Botanical Corrosion Inhibitors in Reinforced Concrete: Material Sustainability Assessment and Analysis - A Review

ABSTRACT

Various methodologies have emerged over the past few decades aimed at controlling and mitigating corrosion. A new field has emerged in controlling corrosion through the use of plant-based corrosion inhibitors. The exploration of botanical extracts' efficacy marks a significant shift in corrosion science, tapping into the potential and utility offered by green plants. This comprehensive study serves as a review encompassing the spectrum of botanical extracts and their applications in diverse contexts concerning reinforced structures. This research critically assesses the correlation between phytochemical compositions, the methodologies employed in solvent extraction, and the adsorption mechanisms pivotal for enhancing the efficacy of plant extracts in corrosion inhibition. The primary objective lies in uncovering the role of inhibitors in safeguarding embedded steel within concrete structures while aiming to curtail corrosion rates. A focal point of this investigation revolves around the transition from employing toxic inhibitors to environmentally friendly botanical extracts for corrosion mitigation. Furthermore, this study accentuates the range of botanical extracts used as corrosion inhibitors shedding light on the specific phytochemical components responsible for driving the corrosion inhibition process. Notably, it expounds upon the future prospects of corrosion inhibitors, outlining the inherent challenges that must be addressed to facilitate their scalability for widespread commercial utilization.

Keywords: Corrosion Inhibitors, performance evaluation, corrosion protection, botanical inhibitors, concrete deterioration.

1. INTRODUCTION

Corrosion is the process of a material eroding attributable to chemical or electrochemical interaction of the environments, leading to material mass loss over some time [1]. Concrete and reinforcing bars are constituents of Reinforced Cement Concrete (RCC) where concrete withstands the compressive strength and the reinforcing bars govern the tensile strength. Presence of corrosion affects the durability of the concrete structures leading to failure of structures in adverse situations. Most of the structures today are made of reinforced bars. The reinforcing

bars used in RCC structures should be good enough to bear tensile strength. When the corrosion starts on one region of the bars the chances of getting corrosion on the other side of the bars gets increase [1]. Due to the rapid deterioration process involved, serviceability criteria design using reinforced bars gets compromised. The corrosion of steel bars induces the concrete to swell, and triggers scaling and fissures in the concrete, resulting in catastrophic events due to compromised performances through structural deterioration [1]. The tendency of a metal to corrode is governed by its microstructures, its composition as generated during alloying, or the temperature developed during manufacturing for the deformation of a single metal surface. It would be more pragmatic to prevent corrosion instead of endeavouring to eliminate it. Corrosion mechanisms can be as diversified as the environments to which

* Corresponding author: Nishant Kumar

E-mail: Nishant.kumar4@sharda.ac.in

Paper received: 15.05.2024.

Paper accepted: 14.06.2024.

Papir is available on the website: www.idk.org.rs/journal

a substance is exposed, which makes them harder to comprehend [1]. However, it can be controlled simply by understanding the mechanisms of a reaction involved in the process. As per the study conducted by CORCON Institute of Corrosion in 2023, the corrosion-related damage and deterioration of structures is responsible for an economic impact of around 4% of the world's GDP annually. In India, this figure can even surpass an estimated 5% of the GDP per year. This is a clear indication about the lack study on protection of concrete structures against corrosion related damages which ultimately leads to reduction in the design life of the structures. The study also revealed that the saving costs can be increased between 15% to 35% of total cost if different corrosion management and controlling practices are followed [2-4]. The cost of corrosion becomes a burden due to its impacts on the economy, the safety of human life, and material resources and energy. Furthermore, the direct and indirect corrosion costs are increased due to ignoring corrosion which adds up to the economic loss for any country. The cost of corrosion as shown in Figure 1 comprises the economic loss and safety of human life [5].




Figure 1. Cost incurred due to corrosion [5]

In Reinforced structures, trillions of dollars have been invested to control the corrosion. Research are going on in finding the best implementable corrosion protection methods [5]. The concept of green corrosion always has better scopes due to its multiple advantages. Furthermore, the efficiency of the green corrosion inhibitors is higher than the toxic organic and inorganic inhibitors. Thousands of green corrosion inhibitors are available that can be used in the form of solutions and paste in the reinforcing bars. The coating can be very effective in different environments ranging from acidic to basic to saline environments. The inhibition efficiency of those natural extracts and eco-friendly materials used in different concentrations is efficacious for use in RC structures [5].

Reinforced Concrete have flaws due to the possibility of corrosion seen in a reinforced bar, this process cannot be reversed rather it can be controlled. The phenomenon of the corrosion process is unpredictable and incalculable. Due to the influence of numerous factors including pH and temperatures, the exact calculation and prediction become difficult [6]. The corrosion behaviour shows contrast in every testing specimen too. So, the tasks become more challenging to find accurate results. The influence of the performances of the materials, and reaction on the environment show a direct impact on the corrosion process. Different preventive techniques have been introduced for a few decades. With the recent advancement in technology, numerous inorganic commercial corrosion inhibitors are available, affirming having the highest efficiency of protection of rebars. Some studies have proved that the use of arsenates, chromates, phosphates molybdates etc. inhibits corrosion in a different medium [7-9]. However, these inhibitors are expensive, non-eco-friendly, and sometimes toxic. Different standards have banned such inhibitors due to their impact on human lives. So, the need for natural inhibitors is seen in more demand due to their multiple advantages over conventional inhibitors. this review attempts to study corrosion and its mechanism in RC structures. In addition, it explains some of the major constituents of different plant-based extracts corrosion inhibitors, their mechanisms of inhibitions, and some plant-based extracts in different environments. Furthermore, this study outlook at using corrosion inhibitors for different applications, including RC structures. The phenomenon involved in corrosion initiation to corrosion inhibition process with different adsorption processes on metal surfaces.

2. LITERATURE OVERVIEW

For a better understanding of the use of corrosion inhibitors in reinforced concrete, an extensive literature review was done and the papers were analysed from 2004 to 2023. As per the database report from Google Scholar, the number of articles published on the use of corrosion inhibitors in reinforced concrete vis-à-vis year is as,

2004-2009: 9,380

2010-2014: 13,200

2015-2019: 16,500 and

2020-2023: 20,100

As evident through the increasing trend in the number of articles published on the use of corrosion inhibitors in concrete, it highlights the ongoing potential for further research in this field. The online database used to search the relevant literature on the use of corrosion inhibitors in reinforced concrete were, Scopus (www.scopus.com) and Web of Science (www.webofscience.com). The keywords that were used to search the literature were “Corrosion Inhibitors”, “corrosion”, “corrosion protection”, “botanical inhibitors”, “durability of concrete” resulted in 203 articles. After scrutinizing and removing the irrel-

evant and duplicate literature 84 articles were selected for the study. The selected papers were classified according to publication year and publication area.

The year-wise distribution of the articles (Figure 2) shows an increase in the number of papers published with each passing year since 2017. However, a decrease in the numbers of papers was observed in the years 2017 and 2015. Also the point to focus is from the year 2019, almost 61% of the total papers used in the study were published in the last 5 years which shows the tremendous potential of the research in this field.




Figure 2. Papers published in last 10 years

The spatial spread of the publications revealed that almost 43% of the research was carried out by India and China, followed by Nigeria, Iran and Mo-

rocco as depicted in Figure 3. Latin America, North America, UK and South East Asia contributed very less to the research.




Figure 3. Spatial spread of the literature survey

3. CORROSION MECHANISM OF EMBEDDED REINFORCEMENT BAR

Corrosion is the inevitable degradation of steel influenced by numerous environmental parameters such as acid, moisture, etc. making it phenomenon more complex. The reactivity of the metal, the presence of inclusions, the availability of oxygen, humidity, gases such as Sulphur dioxide and carbon diox-

ide, and the availability of electrolytes are all factors that induce corrosion. While interlinked capillary porosity makes it very difficult for chloride ions, oxygen, and moisture to permeate concrete fractures and gives a more direct route to react with reinforced bar thus increasing the probability of corrosion [10-12]. Figure 4 explains the corrosion mechanism of reinforced concrete structures.




Figure 4. Corrosion mechanism in Reinforced concrete [12]

Figure 5 explains the various stages of deterioration in concrete due to corrosion of reinforcement. Initially concrete has a pH value of 11-13 which indicates high alkalinity due to the presence of $\text{Ca}(\text{OH})_2$ which protects the reinforcement from corrosion.

Carbonation is a process of chemical reaction of alkaline components in concrete (i.e. $\text{Ca}(\text{OH})_2$) with atmospheric carbon dioxide which enters inside concrete through the surface cracks developed and causes a reduction of pH below 11 [12].




Figure 5. Stages of Deterioration due to corrosion in Reinforced concrete

During the Carbonation process, CO₂ reacts with water or moisture available near structures, since concrete is a permeable material, this gas penetrates concrete cover and reduces alkalinity to 10 or 9, and the passivating layer is damaged and once the passivating layer is damaged, corrosion starts. Once the corrosion starts, rust is formed on the surface of the steel bar which exerts hoop pressure on the surrounding concrete. Due to this continuous hoop pressure, the concrete cracks and eventually spalling of concrete occurs.

The performance of RC structures diminishes as concrete structures deteriorate due to adverse climatic conditions, and the untimely disintegration of structures before the periodic maintenance life is a primary issue for engineers and researchers. The rate at which structures degrade is influenced by the conditions of exposure and the intensity of maintenance. Corrosion, which is triggered by chemical or electrochemical responses, seems to be the most prevalent cause of RC structure deterioration. It is primarily governed by chloride ingress and RC structure carbonation depth. Carbonation and infiltration of chloride ions are the two most common causes of rebar corrosion in concrete constructions. Corrosion of RC structures begins when chloride ions pierce

concrete beyond the predefined threshold or when carbonation depth surpasses concrete cover.

If corrosion commences in concrete structures, it proceeds and diminishes the structures' service life, and the pace of corrosion has an impact on the remaining serviceability of RC structures [13]. Nevertheless, these extreme environments promote reinforcement corrosion unless the requisite concentrations of oxidative degradation are accessible at the rebar level in concrete structures. Corrosion can significantly impair the strength and life of structures, and contaminants from the atmosphere can permeate through the concrete cover and induce corrosion of steel in humid situations. As explained in Figure 6 the cathode and anode are formed in various locations of the same reinforcing bar. Whenever the corrosive process is initiated, the section is degraded in the anodic region. The iron gets transformed into ferrous ionic species, which also are transferred from the anode to the cathode. These regions on the reinforcement bar exhibiting positive electrochemical potential serve as cathode material using moisture, reducing oxygen, and devouring electrons from the anode to form hydroxyl ions. Inside the electrochemical system, the steel bars act as conducting materials, whereas the concrete solution functions as the electrolytic medium whereby the ions migrate [14].




Figure 6. Anode-Cathode formation on steel reinforcement bar [14]

4. CORROSION INHIBITORS

Corrosion inhibitors are additives to concrete that are used to minimize or delay the start of corrosion in reinforced concrete structures. Corrosion inhibitors are substances that, when introduced in minute doses to corrosive environments, avoid or minimize the metal from interacting with it [15]. The

majority of inhibitors stabilize steel by generating a protective layer on its surface; nevertheless, certain inhibitors react with concrete complexes to restrict the concrete's permeability. Corrosion inhibitors are typically incorporated into the normal concrete mixture in modern constructions, but they can also be sprayed on the concrete surface during repairs. Corrosion inhibitors help in reducing the ion's move-

ments within the surfaces which results in slowing down of corrosion process. Furthermore, inhibitors are known to increase the reinforcing bar's cathodic and anodic polarization behavior. The implementation of relevant and effective inhibitors is one of the most appropriate strategies for preserving metals against severe corrosion breakdown [16]. In recent decades, researchers have been looking into the inhibitory capabilities of bioactive antioxidants derived from plants, and they have revealed that they are potent inhibitors. Natural products have the advantage of becoming environmentally friendly and ecologically accepted. Different synthetic inhibitors have serious health consequences, consequently, natural products that seem to be affordable, non-toxic, and environmentally preferable must be used instead [16].

Organic and inorganic inhibitors have shown promising potential in inhibiting efficiency. Different green materials have been studied to understand the nature of the inhibiting action it can bestow for the corrosion-reducing process [17]. The inhibitors inhibit corrosion by increasing anodic or cathodic polarizing behavior, reducing ion mobility on the metallic surface, and raising the metallic surface's electrical resistance [17]. Corrosion inhibitors in concrete have become immensely popular in recent years due to their low cost and accessibility of use in today's scenario, concrete and reinforcing bars have been used worldwide [18].

4.1. Botanical Corrosion Inhibitors

Green Corrosion inhibitors are such inhibitors that serve the purpose of inhibiting corrosion mechanisms without harming human health and environment as they are non-toxic. Botanical corrosion inhibitors are called plant-based extract inhibitors. Due to their abundant availability and being environmentally friendly, the use of corrosion inhibitors has been used widely in different applications [19]. The use of such corrosion inhibitors can add to up structure's life from early deterioration. Using botanical extracts is pertinent for corrosion protection as potential botanical extracts have wide areas of applications. Leaf, roots, fruits, flowers, oil, whole plants, wooden parts including stem, branch, bark, waste, etc. all comprises the parts of plants. All parts of plants have different inhibiting compounds. Different

studies on the materials and the methodology were carried out to understand the potential plant-based extract material.

It showed that the plant has an incredible corrosion inhibition potential. Similarly, the use of curcumin properties of turmeric powder had an inhibiting efficacy of 90% in 0.5M H_2SO_4 on the carbon steel [19]. A similar study was carried out on the use of Xanthan gum in a 15% HCl environment to see the insights of inhibiting efficiency. Experimental data from the lab on mild steel and Density functional theory (DFT) were used for correlation which resulted in better inhibition performances [20]. Furthermore, the use of Xanthan gum as a corrosion inhibitor in aluminium in 0.5 M HCl was also studied and it was observed that the inhibition efficiency was increased while increasing the concentration of gum extract and decreased with an increase in the temperatures [20]. Numeral studies were carried out on plant-based extracts which suggests that the corrosion mechanisms are inhibited when using corrosion inhibitors and are influenced by the substrates. These all-potential plant-based extracts have shown the influence of different adsorption mechanisms in inhibiting efficiency [21-24].

4.2. Phytochemicals in Botanical Extracts

The study of phytochemicals present in the plant-based extract is very important to understand the concentration required for corrosion inhibition for the intended applications [25-28]. Along with this, the study of different phytochemicals helps in understanding which extracts to be used from the plants. The reactivity and the adsorption types involved in the metal substrate help to identify the efficiency of botanical extract corrosion inhibitors. The phenolic acids compounds, terpenoids, carbohydrates, lipids, and alkaloids-based compounds have been proven to be effective in slowing down the corrosion process [26-28]. Figure 7 illustrates the composition of the phytochemicals present in plant-based extracts which are absorbed into the surface of metal following the process of physisorption and chemisorption. Alkaloids and phenolic acids are the most commonly seen phytochemicals in botanical extracts. The combination of different plants-based extracts and their compatibility the similar kinds of phytochemicals can be effective for increasing efficiency [29].

Phenolic Acids	Alkaloids	Terpenoids	Carbohydrates	Lipids
<ul style="list-style-type: none"> • Flavonoids • Phenolic Acids • Xanthones • Quinones • Coumarins • Stilbenoids 	<ul style="list-style-type: none"> • Glucosinolates • Amaryllidaceae • Betalain • Indole • Tropane • Peptide • Purine 	<ul style="list-style-type: none"> • Carotenoids • Monoterpenoids • Lactones • Polyterpenoids 	<ul style="list-style-type: none"> • Monosaccharides • Disaccharides • Polysaccharides • Sugar Alcohol 	<ul style="list-style-type: none"> • Saturated Fats • Fatty Acids • Unsaturated Fats

Figure 7. Phytochemicals present in botanical extract [25-29]

4.3. Solvent Extraction Methods of Botanical Extracts

The identification of phytochemicals with characterizations and quantification of plant-based extraction are done using different types of methodological approaches [30]. Figure 8 comprises both conventional and advanced solving extraction methods which are more commonly used for corrosion inhibitors solvent extractions. Maceration, percolation, decoction, etc. come under the conventional extraction methods. These methods require a higher

volume of solvents with a considerably longer time for extraction. To overcome such problems, greener and advanced extraction methods were introduced like supercritical fluid (SFC), Pressurized Liquid Extraction (PLE), microwave-assisted extraction (MAE), etc. the advantages of using such methods can be as the consumption of organic solvents is lesser and has a very shorter extraction [31-32]. Such advanced methods are very effective in possessing and without losing any of those phytochemical compounds.




Figure 8. Solvent extraction methods of botanical extracts [33]

4.4. Performances of Botanical Extracts

Botanical extracts have been proven to be the best environmental friendly alternative due to their numerous benefits including higher efficiency in different acidic, alkaline, and saline environments [34-44]. Different advanced methods have been employed for corrosion measurement which makes it more efficient [45-61]. The role of inhibitors plays a vital role in the performance of botanical extracts. The parts of plants like leaves, fruit, peel, bark,

seed, root, etc. all can have different performances with different efficiency. Studies revealed that leaf extracts are potential parts for corrosion protection [62-78]. These extracts can inhibit the corrosion process more than the other extracts. Table: 1 in acidic, Table: 2 in alkaline, and Table: 3 in saline environments show some of the potential botanical extracts capable of inhibiting the corrosion process with better efficiency.

Table: 1 Botanical extracts in acidic environment

S. No.	Plants	Parts used	Concentration	Substrate	Medium	Methodology	Efficiency (%)	References
1	Brassica oleracea	Leaves	300 mg/l	Q2355 steel	1 M HCl	XPS, FTIR, UVS, XRD Surface topography	93.8	[34]
2	Neem Leaf	Leaves	4g/200ml	Mild Steel	HCl	WL. Phytochemical test, FTIR, and GCMS	93.24	[35]
3	Solanum Lasiocarpum	Leaves	1g/L	A3 steel	HCl	WLM, PDP, EIS, FTIS, SEM	93.31	[36]
4	Triticum aestivum	straw	4g/L	Stainless Steel (SS-410)	15% HCl	PDP, AFM, XPS, SEM, XRD	92.6	[37]
5	Lilium Brownii	Leaves	200 mg/L	X70 Steel	1M HCl	EIS, FTIR, ECM	85	[38]
6	Green Eucalyptus	Leaves	800 mg/l	Mild Steel	1M HCl	EIS and polarization test	88	[39]
7	Citrullus lanatus	fruit	800 mg/l	Mild steel	1M HCl	PDP, EIS, SEM, AFM	91	[40]
8	Pomelo Peel	Fruit waste	8gm/l	Mild steel	0.1M HCL	PDP, EIS, SEM, FTIR, EDS	74.64	[41]
9	Natural Nutmeg oil	Oil	500 mg/l	L-52 carbon steel	1 M HCl	EIS, WL, ECM	94.73	[42]
10	Glycyrrhiza glabra	leaves	800g/l	Mild Steel	1 M HCl	ECM, surface Characterizations, MD simulations	88%	[43]
11	Cuscuta reflexa	Fruit	500 mg/L	Mild Steel	0.5 M H ₂ SO ₄	UV, FTIR, AFM, SEM, DFT	95.47	[44]
12	Peganum Harmala	Leaves	283.4 g/l	C-Steel	0.25 M H ₂ SO ₄	FTIR, EIS, SEM, UV-spectroscopy	98	[45]
13	Sunflower	Seed hull	400 g/l	Mild steel	1 M HCl	EIS, FTIR, GC analysis and dynamic polarization	98.5	[46]
14	Ginkgo	Leaves	200 mg/l	X 70 steel	1 M HCl	Electrochemical measurements, FE-SEM, AFM	90	[47]
15	Locust bean	Gum	5mM	Q 235 steel	0.5 M H ₂ SO ₄	OCP, PDP, EIS, MDS, QCC	89.8	[48]
16	Tinospora crispa	leaves	8 g/l	Mild Steel	1 M HCl	WLM, PDP, EIS,	80	[49]
17	Punica granatum	leaves	1g/l	Mild steel	1 M HCl	FTIR, XRD, WLM, PDP	94	[50]
18	Gantiana olivieri	Fruit	800mg/l	Mild steel	0.5 M HCl	EIS, HPLC, SEM/EDX	93.7	[51]
19	Tender arecanut	Seed	4.5 g/l	Aluminum	0.5 M HCl	AIS, AFM, electrochemical measurements	94.4	[52]
20	Tagetes erecta	flower	1 g/l	Mild steel	0.5 M H ₂ SO ₄	Gravimetric, PDP, EIS	96.1	[53]
21	Luffa Aegyptiaca	leaf	0.24 g/l	Mild steel	0.5 M H ₂ SO ₄	PDP, FTIR, EIS	93.3	[54]
22	Borage flower	Flower	0.8 g/l	Mild Steel	1 M HCL	WLM, PDP, EIS	91	[55]

23	Red apple (malus domestica)	Fruit	5g/l	Mild steel	0.5M HCL	WLM, PDP, EIS, SEM	87.9	[56]
24	Ammi visnaga	seed	1 g/l	Mild steel	1 M HCl	PDP, EIS	84	[57]
25	Ircinia strobilina	Crude	2g/l	Mild steel	1 M HCl	WLM, PDP, LPR, EIS LC-MS	82	[58]
26	Kappaphycus alvarezii	Thallus	0.5g/l	Mild steel	1 M H ₂ SO ₄	WLM, PDP, EIS, SEM, AFM	79.44	[59]
27	Myristica fragrans	Fruit	0.5g/l	Mild steel	0.5 M H ₂ SO ₄	WLM, EIS, UV, SEM, AFM	87.81	[60]
28	Phyllanthus amarus	Leaves	4% (V/V)	Mild steel	1 M HCl	WLM, Gasometric technique	96.1	[61]
29	Coffea canephora	Seed	1g/l	Carbon steel	1 M HCl	EIS, SEM, WLM, PDP	94	[62]
30	Barley	Whole plant	0.1 g/l	Mild Steel	1 M HCl	WLM, EIS, SEM, PDP	92	[63]
31	Grewa Venusta	Root	8% (v/v)	Mild steel	1 M HCl	AAS, GC-MS, SEM,	97.9	[64]
32	Magnolia grandiflora	Leaves	500 mg/l	Carbon Steel	1 M HCl	WLM, PDP, EIS	88.2	[65]
33	Orange peel waste	Fruit	0.25%	Mild Steel	1 M HCl	WLM, PDP, EIS	95.36	[66]
34	Nigella sativa	seed	0.4 g/l	Mild steel	0.5 M HCL	PDP, EIS	74	[67]
35	Armoracia Rusticana	root	100 mg/l	Mild steel	0.5 M H ₂ SO ₄	WLM, PDP, EIS, FTIR, SEM	95.74	[68]
36	Maesobatrya barteri	Leaves	0.5 g/l	Aluminum	2 M HCl	WLM, Thermometric analysis	45.15	[69]

LC-HRMS: -Liquid chromatography-high resolution mass spectrometry, EIS: Electrochemical impedance Spectroscopy, PDP: - Potentiodynamic polarization, WLM, weight Loss Method, AFM: - Atomic force Microscope , FTIR: - Fourier -Transform infrared spectroscopy, SEM: - Scanning Electron Microscope, MDS: - Molecular Dynamics Simulations , AAS: - Atomic Absorption Spectroscopy, ECM: - Electrochemical Measurement, GC-MS: - Gas Chromatography- Mass Spectrometry, OCP: - Open Circuit Potential, HPLC: - High performance liquid chromatography, UVS:- Ultraviolet Visible Spectroscopy, XRD: - X-ray Powder Diffraction Spectroscopy, LPR: - Linear Polarization Resistance, XPS: - X-ray Photoelectron spectroscopy

Table: 2 Botanical extracts on Alkaline medium

S. No.	Plants	Parts used	Concentration	Substrate	Medium	Methodology	Efficiency (%)	References
1	Henna powder	leaves	50 mg/l	Tin	1 M NaOH	WLS, AIS, TS, SEM	95.97	[70]
2	Arecanut	husk	18 g/l	Mild Steel	0.5 M NaOH	PDP, AFM, SEM, EIS, XRD	91.66	[71]
3	Gossipium hirsutum	Leaves	52% v/v	Aluminum	2 M NaOH	Chemical Techniques, WL	97	[72]
4	(Pentaclethra macrophylla Bentham)	Root	0.3 g/l	Mild Steel	0.5 KOH	WLM, PDP, EIS	91	[73]

Table: 3 Botanical extracts in Saline environments

S. No.	Plants	Parts used	Concentration	Substrate	Medium	Methodology	Efficiency (%)	References
1	Catharanthus roseus	Stem	5mg/l	Mild steel	3.5% NaCl	WLM, PDP, EIS, SEM, XRD, DFT	96	[74]
2	Phyllanthus muellerianus	leaf	0.0833% - 0.416%	Mild steel	3.5% NaCl	WLM, PPS, AIS	97.6	[75]
3	Pomelo peel	Fruit waste	8g/l	Low carbon steel	3.5% NaCl	WLM, SEM, PDP, EDS, EIS, FTIR	71.15	[76]
4	Cascabela Thevetia	leaves	3 g/l	Carbon steel	3.5%NaCl	PDP, EFM, EIS, AFM, OCP	94.4	[77]
5	Echium amoenum fisch	Whole plant	8g/l	ST37 steel	3.5%NaCl	EIS, FTIR, SEM	99.32	[78]

5. CHALLENGES AND FUTURE SCOPE

The use of botanical extracts as corrosion inhibitors in RC structures will have a dominating demand due to their abundant availability, cost-effectiveness, eco-friendly nature, and high efficiency [34-78]. However, for larger commercial purposes, arduous efforts and innumerable challenges comes because of the different parameters involved for the adsorption mechanism facilitating corrosion inhibition [79-81]. The effectiveness of corrosion inhibition properties of various botanical extracts is distinctive [82-84]. Furthermore, the research to prove the inhibition mechanism of all potential plants is still inadequate. In addition to this, the efficient parts of each plant-based extracts exhibit different efficiency and the adsorption mechanisms of each extract are different. The solvent extraction process of extracting the samples becomes expensive when moving toward for commercial use of such inhibitors. The inhibitors inhibiting period, extraction period, storage, etc. makes a challenging task for the use of botanical extracts as corrosion inhibitors. Numerous plants-based extracts which are explored have shown problems of compatibility with other extracts, although some have showed an increase in the inhibiting efficiency but still there is inadequate research on aspects like concentration required for the highest inhibition possible, optimal concentration for compatibility etc. The study on the corrosion-inhibiting phenomena of potential ideal botanical extracts and their combination with other extracts will be beneficial to understand and apply the corrosion inhibitors for intended applications.

Also another area of research can be presence of corrosion inhibitors as coating on the reinforce-

ment bars. As we know that the corrosion occurs on the surface of reinforcement, so there can be a possibility of providing a coating of botanical corrosion inhibitors on the surface of reinforcement to delay or prevent the corrosion. Furthermore, when coatings are provided on the surface of the reinforcement, the coating thickness plays a vital role in development of the bond strength between steel and surrounding concrete. This can be another study area to obtain the optimum coating thickness of the surface applied corrosion inhibitors. The study of corrosion inhibitors in concrete presents diverse and compelling research opportunities that can significantly contribute to the advancement of infrastructure sustainability and durability. One avenue for investigation lies in the comparative analysis of the effectiveness of various corrosion inhibitors employed in concrete. This research can delve into the differences between commonly used inhibitors, such as calcium nitrite, calcium nitrate, organic inhibitors, and silicate-based inhibitors, providing insights into their specific advantages and limitations.

Additionally, there is an opportunity to deepen our understanding of the mechanisms underlying corrosion inhibition in concrete structures. By exploring the molecular and chemical processes at play, researchers can uncover the intricate details of how inhibitors interact with the concrete matrix and prevent corrosion, paving the way for more informed and targeted approaches in inhibitor design and application. Long-term performance assessment is another crucial dimension that warrants exploration. Investigating the durability of corrosion inhibitors over extended periods of exposure to harsh environmental conditions will provide valuable data on the

sustainability of inhibitor treatments and inform maintenance strategies for aging infrastructure.

Furthermore, researchers can explore the compatibility of corrosion inhibitors with various types of concrete mixtures, including high-performance concrete, self-compacting concrete, and lightweight concrete. This line of inquiry can lead to optimized formulations that address the specific needs of different construction scenarios. A holistic approach involves considering the environmental impact of corrosion inhibitors. Assessing the eco-friendliness of inhibitors and their potential effects on the surrounding ecosystem is imperative for sustainable construction practices. Complementing this, a study of inhibitor applications in aggressive environments, such as marine or industrial settings, can provide insights into real-world challenges and opportunities for improvement.

6. CONCLUSION

Corrosion, an inevitable and relentless process, exhibits a complexity influenced by various factors. Countless protective measures have been devised to inhibit corrosion across diverse applications. Among these, the widespread use of efficient corrosion inhibitors stands out. While inorganic corrosion inhibitors demonstrate strong efficacy, their drawbacks, such as limited availability and non-eco-friendly characteristics, render them less than ideal for inhibition purposes. In contrast, botanical extracts as corrosion inhibitors present a promising prospect due to several advantages. These natural extracts are abundantly available and offer higher efficiency while employing environmentally friendly processes. This comprehensive review seeks to highlight the potential of environmentally sustainable corrosion inhibitors within different contexts. It investigates into the significance of phytochemicals present in botanical extracts, explores various solvent extraction methods, and elucidates the adsorption mechanisms utilized to enhance inhibiting efficiency. By focusing on botanical inhibitors and their comparison to toxic inorganic corrosion inhibitors, this study emphasizes the shift towards more eco-conscious solutions. Additionally, it provides an overview of the feasibility and advantages of employing botanical inhibitors across various applications, including their relevance in safeguarding reinforced concrete (RC) structures.

The exploration of botanical extracts as corrosion inhibitors unveils a promising pathway towards

sustainable corrosion prevention strategies. The accessibility of these natural compounds coupled with their increased efficiency in mitigating corrosion showcases a potential alternative to conventional inhibitors. Furthermore, this review aims to draw attention to the pressing need for environmentally viable corrosion inhibition methods, advocating for a shift towards botanical inhibitors as a feasible and eco-friendly solution in combating the pervasive issue of corrosion in diverse settings.

ACKNOWLEDGEMENT

This work is supported by Department of Civil Engineering, School of Engineering and Technology, Sharda University, Greater Noida.

REFERENCES

- [1] O. Abakedi, I. Moses. (2016) Aluminium corrosion inhibition by *Maesobatrya barteri* root extract in hydrochloric acid solution. *American Chemical Science Journal*, 10(3), 1-10. <https://doi.org/10.9734/acscj/2016/21812>.
- [2] Y. Abboud, A. Chagraoui, O. Tanane, A. El Bouari, H. Hannache (2013) Punica granatum leave extract as green corrosion inhibitor for mild steel in Hydrochloric acid. In *MATEC Web of Conferences*, vol. 5, p. 04029. EDP Sciences. <https://doi.org/10.1051/mateconf/20130504029>.
- [3] A. Ahmad, R. Kumar, A. Kumar (2019) Effect of sodium molybdate and sodium tungstate in concrete rebar corrosion. *Anti-Corrosion Methods and Materials*, 66(3), 253-263. <https://doi.org/10.1108/acmm-06-2018-1960>.
- [4] S. Ahmad (2003) Reinforcement corrosion in concrete structures, its monitoring and service life prediction—a review. *Cement and concrete composites*, 25(4-5), 459-471. [https://doi.org/10.1016/s0958-9465\(02\)00086-0](https://doi.org/10.1016/s0958-9465(02)00086-0).
- [5] N. Al Otaibi, H. H. Hammud (2021) Corrosion inhibition using Harmal leaf extract as an Eco-friendly corrosion inhibitor. *Molecules (Basel, Switzerland)*, 26(22), 7024. <https://doi.org/10.3390/molecules26227024>.
- [6] E. Alibakhshi, M. Ramezanzadeh, G. Bahlakeh, B. Ramezanzadeh, M. Mahdavian, M. Motamedi (2018) Glycyrrhiza glabra leaves extract as a green corrosion inhibitor for mild steel in 1 M hydrochloric acid solution: Experimental, molecular dynamics, Monte Carlo and quantum mechanics study. *Journal of Molecular Liquids*, 255, 185–198. <https://doi.org/10.1016/j.molliq.2018.01.144>.
- [7] L. X. Alvarez, O. Troconis de Rincón, J. Escribano, B. C. Rincon Troconis (2023) Organic compounds as corrosion inhibitors for reinforced concrete: a review. *Corrosion Reviews*, 41(6), 617-634. <https://doi.org/10.1515/corrrev-2023-0017>.

- [8] K. K. Anupama, K. Ramya, A. Joseph (2016) Electrochemical and computational aspects of surface interaction and corrosion inhibition of mild steel in hydrochloric acid by *Phyllanthus amarus* leaf extract (PAE). *Journal of Molecular Liquids*, 216, 146–155. <https://doi.org/10.1016/j.molliq.2016.01.019>.
- [9] M. A. Asaad, G. F. Huseien, M. H. Baghban, P. B. Raja, R. Fediuk, I. Faridmehr, F. Alrshoudi (2021) Gum Arabic nanoparticles as green corrosion inhibitor for reinforced concrete exposed to carbon dioxide environment. *Materials*, 14(24), 7867. <https://doi.org/10.3390/ma14247867>.
- [10] H. Ashassi-Sorkhabi, S. Mirzaee, T. Rostamikia, R. Bagheri (2015) Pomegranate (*Punica granatum*) peel extract as a green corrosion inhibitor for mild steel in hydrochloric acid solution. *International Journal of Corrosion*, 2015, 1–6. <https://doi.org/10.1155/2015/197587>.
- [11] S. A. Asipita, M. Ismail, M. Z. Abd Majid, Z. A. Majid, C. Abdullah, J. Mirza, (2014) Green *Bambusa Arundinacea* leaves extract as a sustainable corrosion inhibitor in steel reinforced concrete. *Journal of Cleaner Production*, 67, 139-146. <https://doi.org/10.1016/j.jclepro.2013.12.033>.
- [12] S. A. Austin, R. Lyons, M. J. Ing (2004) Electrochemical behavior of steel-reinforced concrete during accelerated corrosion testing. *Corrosion*, 60(2), 203-212. <https://doi.org/10.5006/1.3287722>.
- [13] E. Baran, A. Cakir, B. Yazici (2019) Inhibitory effect of *Gentiana olivieri* extracts on the corrosion of mild steel in 0.5 M HCl: Electrochemical and phytochemical evaluation. *Arabian Journal of Chemistry*, 12(8), 4303–4319. <https://doi.org/10.1016/j.arabj.2016.06.008>.
- [14] M. Barbouchi, B. Benzidia, A. Aouidate, A. Ghaleb, M. El Idrissi (2020) Theoretical modeling and experimental studies of Terebinth extracts as green corrosion inhibitor for iron in 3% NaCl medium. *Journal of King Saud University-Science*, 32(7), 2995-3004. <https://doi.org/10.1016/j.jksus.2020.08.004>.
- [15] N. Bhardwaj, P. Sharma, V. Kumar (2021) *Triticum aestivum* extract as corrosion inhibitor for stainless steel (SS-410) in acidic media: Experimental and theoretical study. *Current Research in Green and Sustainable Chemistry*, 4(100189), 100189. <https://doi.org/10.1016/j.crgsc.2021.100189>.
- [16] T.K. Bhuvaneshwari, P. Arulmathi (2020) Corrosion inhibition of mild steel in hydrochloric acid by leaves extract of *Tephrosia purpurea*. *Journal of Adhesion Science and Technology*, 34(22), 2424-2447. <https://doi.org/10.1080/01694243.2020.1766395>.
- [17] A. Biswas, P. Mourya, D. Mondal, S. Pal, G. Udayabhanu (2018) Grafting effect of gum acacia on mild steel corrosion in acidic medium: Gravimetric and electrochemical study. *Journal of Molecular Liquids*, 251, 470–479. <https://doi.org/10.1016/j.molliq.2017.12.087>.
- [18] A. Biswas, S. Pal, G. Udayabhanu (2016) Xanthan Gum and Gum Acacia as corrosion inhibitor for mild steel in 15% HCl medium. *Proceedings of the International Conference on Nanotechnology for Better Living*. <https://doi.org/10.3850/978-981-09-7519-7nbl16-rps-70>.
- [19] A. Biswas, S. Pal, G. Udayabhanu (2015) Experimental and theoretical studies of xanthan gum and its graft co-polymer as corrosion inhibitor for mild steel in 15% HCl. *Applied surface science*, 353, 173-183. <https://doi.org/10.1016/j.apsusc.2015.06.128>.
- [20] Y. Cao, C. Zou, C. Wang, W. Chen, H. Liang, S. Lin (2021) Green corrosion inhibitor of β -cyclodextrin modified xanthan gum for X80 steel in 1 M H₂SO₄ at different temperature. *Journal of Molecular Liquids*, 341, 117391. <https://doi.org/10.1016/j.molliq.2021.117391>.
- [21] S. Chen, S. Chen, B. Zhu, C. Huang, W. Li (2020) *Magnolia grandiflora* leaves extract as a novel environmentally friendly inhibitor for Q235 steel corrosion in 1 M HCl: Combining experimental and theoretical researches. *Journal of Molecular Liquids*, 311(113312), 113312. <https://doi.org/10.1016/j.molliq.2020.113312>.
- [22] L. J. Dacio, O. M. Troconis de Rincon, L. X. Alvarez, H. Castaneda, L. Quesada Román, B. C. Rincon Troconis (2023) Evaluating 1-Benzyl-4-Phenyl-1H-1, 2, 3-Triazole as a Green Corrosion Inhibitor in a Synthetic Pore Solution to Protect Steel Rebars. *Corrosion*, 79(4), 405-418. <https://doi.org/10.5006/4207>.
- [23] A. Dehghani, G. Bahlakeh, B. Ramezanzadeh, M. Ramezanzadeh (2019) A combined experimental and theoretical study of green corrosion inhibition of mild steel in HCl solution by aqueous *Citrullus lanatus* fruit (CLF) extract. *Journal of Molecular Liquids*, 279, 603–624. <https://doi.org/10.1016/j.molliq.2019.02.010>.
- [24] R. Dharmaraj, S. R. Samuyktha, K. Thansiya, S. S. Manzoor, B. N. Kumar, S. Maruvarasan (2021) Turkey berries leaves extract as corrosion inhibitor embedded steel in concrete. In *IOP Conference Series: Materials Science and Engineering* (Vol. 1145, No. 1, p. 012073). IOP Publishing. <https://doi.org/10.1088/1757-899x/1145/1/012073>.
- [25] P. Divya, S. Subhashini, A. Prithiba, R. Rajalakshmi (2019) *Tithonia Diversifolia* flower Extract as green Corrosion Inhibitor for Mild Steel in Acid Medium. *Materials Today: Proceedings*, 18, 1581–1591. <https://doi.org/10.1016/j.matpr.2019.05.252>.
- [26] G. Fekkar, F. Yousfi, H. Elmsellem, M. Aiboudi, M. Ramdani, I. Abdel-Rahman, L. Bouyazza (2020) Eco-friendly *Chamaerops humilis* L. fruit extract corrosion inhibitor for mild steel in 1 M HCl. *International Journal of Corrosion and Scale Inhibition*, 9(2), 446-459. <https://doi.org/10.17675/2305-6894-2020-9-2-4>.
- [27] C. M. Fernandes, T. Ferreira Fagundes, N. Escarpini dos Santos, T. Shewry de M. Rocha, R. Garrett, R. M. Borges, E. A. Ponzio (2019) *Ircinia strobilina* crude extract as corrosion inhibitor for mild steel in acid medium. *Electrochimica Acta*, 312, 137–148. <https://doi.org/10.1016/j.electacta.2019.04.148>.

- [28] G. A. Gaber, M. M. Ghobashy, M. Madani, D. M. Alshangiti, S. A. Alkhursani, S. A. Al-Gahtany, N. Nady (2021) Study of the corrosion-inhibiting activity of the green materials of the *Posidonia oceanica* leaves' ethanolic extract based on PVP in corrosive media (1 M of HCl). *Green Processing and Synthesis*, 10(1), 555–568. <https://doi.org/10.1515/gps-2021-0055>.
- [29] K. M. O. L. Goni, M. A. Mazumder (2019) Green corrosion inhibitors. *Corrosion inhibitors*, 30(4), 77-83. <https://doi.org/10.5772/intechopen.81376>.
- [30] L. Guo, R. Zhang, B. Tan, W. Li, H. Liu, S. Wu (2020) Locust Bean Gum as a green and novel corrosion inhibitor for Q235 steel in 0.5 M H₂SO₄ medium. *Journal of Molecular Liquids*, 310(113239), 113239. <https://doi.org/10.1016/j.molliq.2020.113239>.
- [31] Z. A. Hadi, A. S. Mahdi, S. S. Bahar (2020) Reed Leaves Extract as Corrosion Inhibitor for Reinforcing Steel in Concrete. In *IOP Conference Series: Materials Science and Engineering* (Vol. 871, No. 1, p. 012003). IOP Publishing. <https://doi.org/10.1088/1757-899x/871/1/012003>.
- [32] R. Haldhar, D. Prasad, A. Saxena (2018a) *Armoracia rusticana* as sustainable and eco-friendly corrosion inhibitor for mild steel in 0.5M sulphuric acid: Experimental and theoretical investigations. *Journal of Environmental Chemical Engineering*, 6(4), 5230–5238. <https://doi.org/10.1016/j.jece.2018.08.025>.
- [33] R. Haldhar, D. Prasad, A. Saxena (2018b) *Myristica fragrans* extract as an eco-friendly corrosion inhibitor for mild steel in 0.5 M H₂SO₄ solution. *Journal of Environmental Chemical Engineering*, 6(2), 2290–2301. <https://doi.org/10.1016/j.jece.2018.03.023>.
- [34] H. Hassannejad, A. Nouri (2018) Sunflower seed hull extract as a novel green corrosion inhibitor for mild steel in HCl solution. *Journal of Molecular Liquids*, 254, 377–382. <https://doi.org/10.1016/j.molliq.2018.01.142>.
- [35] B. Hou (2019) *The Cost of Corrosion in China*. Springer Singapore. <https://doi.org/10.1007/978-981-32-9354-0>.
- [36] M. H. Hussin, M. Jain Kassim, N. N. Razali, N. H. Dahon, D. Nasshorudin (2016) The effect of *Tinospora crispa* extracts as a natural mild steel corrosion inhibitor in 1M HCl solution. *Arabian Journal of Chemistry*, 9, S616–S624. <https://doi.org/10.1016/j.arabjc.2011.07.002>.
- [37] S. Jyothi, J. Ravichandran (2014) *Luffa aegyptiaca* leaves extract as corrosion inhibitor for mild steel in hydrochloric acid medium. *Journal of Adhesion Science and Technology*, 28(22-23), 2347-2363. <https://doi.org/10.1080/01694243.2014.966886>.
- [38] C. Kamal, M. G. Sethuraman (2014) *Kappaphycus alvarezii*—A marine red alga as a green inhibitor for acid corrosion of mild steel. *Materials and Corrosion*, 65(8), 846-854. <https://doi.org/10.1002/maco.201307089>.
- [39] A. Khadraoui, A. Khelifa, H. Hamitouche, R. Mehdaoui (2014) Inhibitive effect by extract of *Mentha rotundifolia* leaves on the corrosion of steel in 1 M HCl solution. *Research on Chemical Intermediates*, 40(3), 961–972. <https://doi.org/10.1007/s11164-012-1014-y>.
- [40] M. Khan, M. M. S. Abdullah, A. Mahmood, A. M. Al-Mayouf, H. Z. Alkhathlan (2019) Evaluation of *Matricaria aurea* extracts as effective anti-corrosive agent for mild steel in 1.0 M HCl and isolation of their active ingredients. *Sustainability*, 11(24), 7174. <https://doi.org/10.3390/su11247174>.
- [41] D. S. Kharitonov, M. Zimowska, J. Ryl, A. Zieliński, M. A. Osipenko, J. Adamiec, A. Wrzesińska, P. M. Claesson, I. I. Kurilo (2021) Aqueous molybdate provides effective corrosion inhibition of WE43 magnesium alloy in sodium chloride solutions. *Corrosion Science*, 190, 109664. <https://doi.org/10.1016/j.corsci.2021.109664>.
- [42] N. Kumar, S. Saharan (2022) Use of *Lawsonia inermis* and sodium nitrite as surface applied corrosion inhibitors. *International Journal of Sustainable Construction Engineering and Technology*, 13(1), 1-8. <https://doi.org/10.30880/ijscet.2022.13.01.001>.
- [43] N. Kumar, B. Chalisey, S. Saharan, M. Gupta (2019) Effect of Surface Applied Organic and Inorganic Corrosion Inhibitors on Reinforced Steel in Concrete. *International Journal of Engineering and Advanced Technology*, 9(2), 3023-3031. <https://doi.org/10.35940/ijeat.b4092.129219>.
- [44] N. Kumpawat, A. Chaturvedi, R. K. Upadhyay (2012) Comparative study of corrosion inhibition efficiency of naturally occurring ecofriendly varieties of holy basil (Tulsi) for tin in HNO₃ Solution. *Open Journal of Metal*, 02(03), 68–73. <https://doi.org/10.4236/ojmetal.2012.23010>.
- [45] H. Li, Y. Qiang, W. Zhao, S. Zhang (2021) A green *Brassica oleracea L* extract as a novel corrosion inhibitor for Q235 steel in two typical acid media. *Colloids and Surfaces. A, Physicochemical and Engineering Aspects*, 616(126077), 126077. <https://doi.org/10.1016/j.colsurfa.2020.126077>.
- [46] J. O. Madu, C. Ifeakachukwu, U. Okorodudu, F. V. Adams, I. V. Joseph (2019) Corrosion inhibition efficiency of *Terminalia catappa* leaves extracts on stainless steel in hydrochloric acid. *Journal of Physics. Conference Series*, 1378(2), 022092. <https://doi.org/10.1088/1742-6596/1378/2/022092>.
- [47] F. M. Mahgoub, A. M. Hefnawy, E. H. Abd Alrazzaq (2019) Corrosion inhibition of mild steel in acidic solution by leaves and stem extract of *Acacia nilotica*. *Desalination and Water Treatment*, 169, 49-58. <https://doi.org/10.5004/dwt.2019.24681>.
- [48] I. Manciualea, C. Bogatu, E. Comanita, A. Duta, L. Dumitrescu (2009) Mannich basis - corrosion inhibitors in saline water. *Environmental Engineering and Management Journal*, 8(4), 877–882. <https://doi.org/10.30638/eemj.2009.125>.
- [49] A. L. Matilla, M. I. P. Barrio, A. C. Escamilla, J. P. Ferrer, T. G. Prieto (2024) Analysis of the Effectiveness of the Application of Corrosion Inhibitors to Steel Re-Bars Embedded in Concrete. *Applied Sciences*, 14(8), 3364. <https://doi.org/10.3390/app14083364>.

- [50] Z. V. P. Murthy, K. Vijayaragavan (2014) Mild steel corrosion inhibition by acid extract of leaves of *Hibiscus sabdariffa* as a green corrosion inhibitor and sorption behavior. *Green Chemistry Letters and Reviews*, 7(3), 209-219. <https://doi.org/10.1080/17518253.2014.924592>.
- [51] N. A. Odewunmi, S. A. Umoren, Z. M. Gasem, S. A. Ganiyu, Q. Muhammad (2015) L-Citrulline: An active corrosion inhibitor component of watermelon rind extract for mild steel in HCl medium. *Journal of the Taiwan Institute of Chemical Engineers*, 51, 177-185. <https://doi.org/10.1016/j.jtice.2015.01.012>.
- [52] J. O. Okeniyi, A. P. I. Popoola, E. T. Okeniyi (2018) *Cymbopogon citratus* and NaNO_2 Behaviours in 3.5% NaCl-Immersed Steel-Reinforced Concrete: Implications for Eco-Friendly Corrosion Inhibitor Applications for Steel in Concrete. *International Journal of Corrosion*, 2018, 1-11. <https://doi.org/10.1155/2018/5949042>.
- [53] A. Okewale, F. Omoruwu (2018) Neem leaf extract as a corrosion inhibitor on mild steel in acidic solution. *International Journal of Engineering Research in Africa*, 35, 208-220. <https://doi.org/10.4028/www.scientific.net/jera.35.208>.
- [54] M. A. Omran, M. Fawzy, A. E. D. Mahmoud, O. A. Abdullatef (2022) Optimization of mild steel corrosion inhibition by water hyacinth and common reed extracts in acid media using factorial experimental design. *Green Chemistry Letters and Reviews*, 15(1), 216-232. <https://doi.org/10.1080/17518253.2022.2032844>.
- [55] O. Oyewole, B. T. Ogunsemi, A. Akinmoladun, T. Oshin, J. Adeoye, P. Otowo, A. Tunbosun, T. Oreofe (2024) Performance Evaluation of Bryophyllum Leaves Extract as Corrosion Inhibitor for Mild Steel in 1M Phosphoric Acid. <https://doi.org/10.21203/rs.3.rs-3996094/v1>.
- [56] A. Pal, C. Das (2022) New eco-friendly anti-corrosion inhibitor of purple rice bran extract for boiler quality steel: Experimental and theoretical investigations. *Journal of Molecular Structure*, 1251, 131988. <https://doi.org/10.1016/j.molstruc.2021.131988>.
- [57] G. Palumbo, K. Berent, E. Proniewicz, J. Banaś (2019) Guar gum as an eco-friendly corrosion inhibitor for pure aluminium in 1-M HCl solution. *Materials*, 12(16), 2620. <https://doi.org/10.3390/ma12162620>.
- [58] D. A. Pineda Hernández, E. Restrepo Parra, P. J. Arango Arango, B. Segura Giraldo, C. D. Acosta Medina (2021) Innovative method for coating of natural corrosion inhibitor based on *Artemisia vulgaris*. *Materials*, 14(9), 2234. <https://doi.org/10.3390/ma14092234>.
- [59] Y. Qiang, S. Zhang, B. Tan, S. Chen (2018) Evaluation of Ginkgo leaf extract as an eco-friendly corrosion inhibitor of X70 steel in HCl solution. *Corrosion Science*, 133, 6-16. <https://doi.org/10.1016/j.corsci.2018.01.008>.
- [60] P. B. Raja, M. G. Sethuraman (2008) Natural products as corrosion inhibitor for metals in corrosive media—a review. *Materials letters*, 62(1), 113-116. <https://doi.org/10.1016/j.matlet.2007.04.079>.
- [61] S. Z. Salleh, A. H. Yusoff, S. K. Zakaria, M. A. A. Taib, A. Abu Seman, M. N. Masri, M. Mohamad, S. Mamat, S. Ahmad Sobri, A. Ali, P. T. Teo (2021) Plant extracts as green corrosion inhibitor for ferrous metal alloys: A review. *Journal of Cleaner Production*, 304, 127030. <https://doi.org/10.1016/j.jclepro.2021.127030>.
- [62] É. Santos, R. Cordeiro, M. Santos, P. R. P. Rodrigues, A. Singh, E. D'Elia (2019) Barley Agro-industrial residues as corrosion inhibitor for mild steel in 1mol L-1HCl solution. *Materials Research*, 22(2). <https://doi.org/10.1590/1980-5373-mr-2018-0511>.
- [63] A. Saxena, D. Prasad, R. Haldhar (2018) Investigation of corrosion inhibition effect and adsorption activities of *Cuscuta reflexa* extract for mild steel in 0.5 M H_2SO_4 . *Bioelectrochemistry (Amsterdam, Netherlands)*, 124, 156-164. <https://doi.org/10.1016/j.bioelechem.2018.07.006>.
- [64] A. Saxena, D. Prasad, R. Haldhar, G. Singh, A. Kumar (2018) Use of *Saraca ashoka* extract as green corrosion inhibitor for mild steel in 0.5 M H_2SO_4 . *Journal of Molecular Liquids*, 258, 89-97. <https://doi.org/10.1016/j.molliq.2018.02.104>.
- [65] K. Shanmuga priya, B. S. Prathibha, V. G. Vasudha, H. P. Nagaswarupa (2018) *Spathodea campanulata* as a corrosion inhibitor for mild steel in 1N H_2SO_4 media. *Materials Today: Proceedings*, 5(10), 22595-22604. <https://doi.org/10.1016/j.matpr.2018.06.633>.
- [66] P. R. Shrestha, H. B. Oli, B. Thapa, Y. Chaudhary, D. K. Gupta, A. K. Das, A. P. Yadav (2019) Bark extract of *Lantana camara* in 1M HCl as green corrosion inhibitor for mild steel. *Warasan Witsawakamsat. Chulalongkorn University*, 23(4), 205-211. <https://doi.org/10.4186/ej.2019.23.4.205>.
- [67] E. C. Souza, B. Ripper, D. Perrone, E. D'Elia (2016) Roasted coffee extracts as corrosion inhibitors for mild steel in HCL solution. *Materials Research*, 19(6), 1276-1285. <https://doi.org/10.1590/1980-5373-mr-2015-0740>.
- [68] T. A. Söylev, M. G. Richardson (2008) Corrosion inhibitors for steel in concrete: State-of-the-art report. *Construction and Building Materials*, 22(4), 609-622. <https://doi.org/10.1016/j.conbuildmat.2006.10.013>.
- [69] M. Tariq Saeed, M. Saleem, A. H. Niyazi, F. A. Al-Shamrani, N. A. Jazzar, M. Ali (2020) Carrot (*Daucus carota* L.) peels extract as an herbal corrosion inhibitor for mild steel in 1M HCl solution. *Modern Applied Science*, 14(2), 97. <https://doi.org/10.5539/mas.v14n2p97>.
- [70] A. Thomas, M. Prajila, K. M. Shainy, A. Joseph (2020) A green approach to corrosion inhibition of mild steel in hydrochloric acid using fruit rind extract of *Garcinia indica* (Binda). *Journal of Molecular Liquids*, 312(113369), 113369. <https://doi.org/10.1016/j.molliq.2020.113369>.
- [71] Y. Tian, J. Bao, D. Xie, B. Wang, P. Zhang, T. Zhao, D. Lei (2023) The effects of organic corrosion inhibi-

- tor on concrete properties and frost resistance. *Journal of Building Engineering*, 65, 105762. <https://doi.org/10.1016/j.jobte.2022.105762>.
- [72] İ. B. Topçu, A. Uzunömeroğlu (2020) Properties of corrosion inhibitors on reinforced concrete. *Journal of Structural Engineering and Applied Mechanics*, 3(2), 93–109. <https://doi.org/10.31462/jseam.2020.02093109>.
- [73] S. Umoren, I. B. Obot, Z. Gasem, N. A. Odewunmi (2015) Experimental and theoretical studies of Red Apple fruit extract as green corrosion inhibitor for mild steel in HCl solution. *Journal of Dispersion Science and Technology*, 36(6), 789–802. <https://doi.org/10.1080/01932691.2014.922887>.
- [74] B. Valdez-Salas, R. Vazquez-Delgado, J. Salvador-Carlos, E. Beltran-Partida, R. Salinas-Martinez, N. Cheng, M. Curiel-Alvarez (2021) Azadirachta indica leaf extract as green corrosion inhibitor for reinforced concrete structures: corrosion effectiveness against commercial corrosion inhibitors and concrete integrity. *Materials*, 14(12), 3326. <https://doi.org/10.3390/ma14123326>.
- [75] K. K. Veedu, T. P. Kalarikkal, N. Jayakumar, N. K. Gopalan (2019) Anticorrosive performance of Mangifera indica L. Leaf extract-based hybrid coating on steel. *ACS omega*, 4(6), 10176. <https://doi.org/10.1021/acsomega.9b00632>.
- [76] X. Wang, H. Jiang, D. X. Zhang, L. Hou, W. J. Zhou (2019) Solanum lasiocarpum L. extract as green corrosion inhibitor for A3 steel in 1 M HCl solution. *International Journal of Electrochemical Science*, 14(2), 1178–1196. <https://doi.org/10.20964/2019.02.06>.
- [77] S. A. Xavier Stango, U. Vijayalakshmi (2018) Studies on corrosion inhibitory effect and adsorption behavior of waste materials on mild steel in acidic medium. *Journal of Asian Ceramic Societies*, 6(1), 20–29. <https://doi.org/10.1080/21870764.2018.1439608>.
- [78] B. Yang, W. Chen, D. H. Mu (2014) Study of garlic extract as a green corrosion inhibitor for mild steel in acidic media. *Advanced Materials Research*, 960, 118–125. <https://doi.org/10.4028/www.scientific.net/amr.960-961.118>.
- [79] Y. P. Yee, S. N. Saud, E. Hamzah (2020) Pomelo peel extract as corrosion inhibitor for steel in simulated seawater and acidic mediums. *Journal of Materials Engineering and Performance*, 29(4), 2202–2215. <https://doi.org/10.1007/s11665-020-04774-1>.
- [80] A. Zaher, R. Aslam, H. S. Lee, A. Khafouri, M. Boufelous, A. A. Alrashdi, M. Ouhssine (2022) A combined computational & electrochemical exploration of the Ammi visnaga L. extract as a green corrosion inhibitor for carbon steel in HCl solution. *Arabian Journal of Chemistry*, 15(2), 103573. <https://doi.org/10.1016/j.arabjc.2021.103573>.
- [81] H. Zhang, Z. Ni, H. Wu, P. Xu, Z. Li, W. Zhang, H. Huang, Q. Zhou, X. Yue, J. Bao, X. Li (2020) Corrosion Inhibition of Carbon Steel in Hydrochloric Acid by Chrysanthemum Indicum Extract. *International Journal of Electrochemical Science*, 15(6), 5487–5499. <https://doi.org/10.20964/2020.06.22>.
- [82] A. Zhao, H. Sun, L. Chen, Y. Huang, X. Lu, B. Mu, H. Gao, S. Wang, A. Singh (2019) Electrochemical Studies of Bitter Gourd (Momordica charantia) fruits as Ecofriendly Corrosion Inhibitor for Mild Steel in 1 M HCl Solution. *International Journal of Electrochemical Science*, 14(7), 6814–6825. <https://doi.org/10.20964/2019.07.75>.
- [83] X. Zheng, M. Gong, Q. Li, L. Guo (2018) Corrosion inhibition of mild steel in sulfuric acid solution by loquat (Eriobotrya japonica Lindl.) leaves extract. *Scientific reports*, 8(1), 9140. <https://doi.org/10.1038/s41598-018-27257-9>.
- [84] X. Zuo, W. Li, W. Luo, X. Zhang, Y. Qiang, J. Zhang, H. Li, B. Tan (2021) Research of Liliium brownii leaves extract as a commendable and green inhibitor for X70 steel corrosion in hydrochloric acid. *Journal of Molecular Liquids*, 321, 114914. <https://doi.org/10.1016/j.molliq.2020.114914>.

IZVOD

BILJNI INHIBITORI KOROZIJE U ARMIRANOM BETONU: PROCENA I ANALIZA ODRŽIVOSTI MATERIJALA - PREGLED

Tokom proteklih nekoliko decenija pojavile su se različite metodologije koje imaju za cilj kontrolu i ublažavanje korozije. Pojavilo se novo polje u kontroli korozije upotrebom inhibitora korozije na bazi biljaka. Istraživanje efikasnosti botaničkih ekstrakata označava značajan pomak u nauci o koroziji, koristeći potencijal i korisnost zelenih biljaka. Ova sveobuhvatna studija služi kao pregled koji obuhvata spektar botaničkih ekstrakata i njihovu primenu u različitim kontekstima u vezi sa ojačanim strukturama. Ovo istraživanje kritički procenjuje korelaciju između fitohemijskih sastava, metodologija korišćenih u ekstrakciji rastvaračem i mehanizama adsorpcije, koji su ključni za povećanje efikasnosti biljnih ekstrakata u inhibiciji korozije. Primarni cilj leži u otkrivanju uloge inhibitora u zaštiti ugrađenog čelika unutar betonskih konstrukcija sa ciljem smanjenja stope korozije. Fokus ovog istraživanja je oko prelaska sa upotrebe toksičnih inhibitora na ekološki prihvatljive botaničke ekstrakte za ublažavanje korozije. Štaviše, ova studija naglašava niz botaničkih ekstrakata koji se koriste kao inhibitori korozije, bacajući svetlo na specifične fitohemijske komponente odgovorne za pokretanje procesa inhibicije korozije. Naročito, objašnjava buduće izgleda inhibitora korozije, naglašavajući inherentne izazove koji se moraju rešiti da bi se olakšala njihova skalabilnost za široku komercijalnu upotrebu.

Ključne reči: Inhibitori korozije, ocena performansi, zaštita od korozije, biljni inhibitori, propadanje betona.

Pregledni rad

Rad primljen: 15.05.2024.

Rad prihvaćen: 14.06.2024.

The ORCID Ids of all the authors are as follows:

Nishant Kumar: <https://orcid.org/0000-0001-5477-3293>

Ikhwan Syafiq Mohd Noor: <https://orcid.org/0000-0003-0983-782X>

Muhd Zu Azhan Yahya: <https://orcid.org/0000-0003-1129-0552>

Satya Prakash: <https://orcid.org/0000-0001-6633-7480>